## PATENT SPECIFICATION

NO DRAWINGS

1.053.331

1053,331



Date of Application and filing Complete Specification: March 4, 1964.
No. 9119/64.

Application made in Germany (No. E24436 VIIId/21c) on March 5, 1963. Complete Specification Published: Dec. 30, 1966.

© Crown Copyright 1966.

Index at acceptance: —H1 K(1D4P, 1D4X, 2R4, 2RX, 2S6, 2S8, 5M)

Int. Cl.: -H 01 c 7/00

## COMPLETE SPECIFICATION

## Electrical Resistance Material

We, ELOFOL A.G., a Liechtenstein company, of Vaduz, Liechtenstein, do hereby declare the invention, for which we pray that a Patent may be granted to us, and the method by which it is to be performed, to be particularly described in and by the following statement:—

The invention relates to an electrical resistance material for the production of resistors, so especially laminated resistors, for heating purposes, which comprises a finely divided resistance substance, for example graphite or a finely divided resistance wire alloy, the substance being embedded in and thus bonded by an inert carrier material, for example a synthetic resin or lacquer. By inert carrier material is meant a substance which undergoes no chemical reaction with the other consultuents of the resistance material and takes practically no part in the electrical conductivity of the resistance material.

Laminated resistors, which contain graphite, carbon black, metal dust or other conductive substance as the resistance substance solidified with a binder, are known. If these resistors are to be used as heating resistors they require special devices such as thermostats to regulate the remperature and keep it constant as well as to prevent overloading of the re-

Laminated resistors made of graphite bonded by synthetic resin are particularly easy to manufacture owing to their simplicity, but have the disadvantage that owing to the negative temperature coefficient of this resistance substance, they take up more current when heated and therefore become still hotter. If any circumstances arise to reduce heat transfer, for example if a piece of furniture is placed in front of the laminated resistor, there is the danger that the resistor itself will be overheated and burnt, which not only destroys the resistor but may cause a fire. For this reason it has not been possible to

use graphite resistors of large surface area for hearing purposes. But even in a resistor in which metal powder is used as the resistance substance, the reduction is current consumption which occurs when the resistor is heated, since it has a positive temperature coefficient, is frequently not sufficient to ensure that the resistor will not burn, because the heat transfer may be insufficient.

It is an important problem, particularly for a heating resistor of large surface area, to find an arrangement by which the resistor is not controlled as a whole, for example by being switched on and off by a thermostat, but which ensures that every minute individual area of the resistor will automatically adjust itself according to the temperature load to which it is subjected, and thus adjust its resistance. Such a heating resistor having for example a surface area of 1 square metre would thus have the same resistance value over its whole surface except over a small area of, for example, 100 square centimetres in which transfer of heat may be in some way prevented, where it would have a higher resistance value and where after a slight and quite permissible increase in temperature the heat produced would be considerably diminished.

It is an object of the invention to provide an electrical resistance material which, whilst avoiding the above-mentioned disadvantages, requires no temperature regulating device but alters its resistance value in each unit area of a resistor according to the thermal stress in that area, so that the current consumption and hence the electrical power in that area will not permit the temperature in that to rise above a maximum value depending on the working temperature of the material as a whole, so that localised burning will be

According to this invention, an electric resistance material has the following con-

[,

stituents:— a finely divided resistance substance, an insulating material, and a nonconductive inert carrier material, the insulating material having a markedly higher specific resistance and a greater coefficient of thermal expansion than the resistance substance such that when the resistance material is heated the insulating material expands to a greater extent than the resistance substance and thus increases the resistance to current flow between the particles of resistance substance.

It is essential that, in the resistance material of the invention, the resistance substance, the insulating material and the carrier material 15 be clearly separate and distinct components of the resistance material and not interchangeable. In contradistinction to this essential requirement, a resistance material is known having only two clearly separate and distinct components, viz. a resistance substance and a thermally expansible non-conductive carrier material of special properties. It is also known that the latter carrier material may have two constituents, for example polyethylene and polyterrafluoroethylene, but these constituents form a mixed synthetic material acting as a unitary whole to give a special thermally expansible property; they do not act separately in so far as their insulating properties are concerned.

If the finely divided resistance substance is metallic and has a positive temperature coefficient, the temperature coefficient of the resistance material will be of a greater value than that which would be expected from the temperature coefficient of the metal, whereby a resistor made of the resistance material is rendered considerably morefireproof. Further, if graphite or other resistance substance with a negative temperature coefficient is used, which is in itself an advantage, the negative temperature coefficient is as it were converted into a positive temperature coefficient of the resistance material as a whole and it is only by virtue of this that the use of graphite as a resistance substance, with its attendant advantages, becomes possible at all. When there is a rise in temperature of a

whole or a part of a resistor, e.g. in the form 50 of a foil made of the resistance material, the insulating material takes up a larger volume than the resistance substance so that either the conract between the individual particles of the resistance substance is impaired due to the fact that they are forced apart by the expanding particles of insulating material or the insulating material, for example if it is liquid, will be forced between the individual particles of the resistance substance and thus considerably increase the resistance to current flow between these particles. The resistance value of such a resistor will thus vary from point to point according to the temperature at each point, so 65 that such a resistor, which is particularly suitable for heating, can be regarded as a resistor controlled by a large number of individual thermostats in each minute area.

A particular advantage which provides for simple manufacture of a resistor and advantageous electrical behaviour is achieved if the insulating material is liquid below a desired maximum temperature of the resistor, and preferably even at the working temperature, or becomes liquid at that temperature, or at least softens to such an extent that it can undergo plastic deformation. In that case, the insulating material is added to the resistance substance before the latter is introduced into the inert carrier material. In a resistor produced in this way, the insulating material in use is pushed between the individual particles of resistance substance as it becomes soft under increased thermal stress, thereby increasing the resistance to 85 current flow between the particles.

If a solid substance such as glass powder is used as the insulating material, the introduction of the finely divided resistance substance and of the insulating material into the inert carrier material may be carried out in

any desired sequence.

For practical use, graphite powder and finely divided iron alloys (resistance wire alloys) have proved to be suitable resistance 95 substances. Suitable for use as the insulating material is any material whose specific resistance is markedly above that of the resistance substance, e.g. materials having a resistivity of 10° Ohm cm. when graphite 100 with a resistivity of 8.10° Ohm cm. is used, and which have a greater coefficient of thermal expansion than the resistance substance.

For the manufacture of the resistors, the 105 resistance material may be applied to an additional rigid or flexible carrier. Alternatively, such a carrier may be partly or completely impregnated with the resistance material. Alternatively, the resistance material may be formed into a self-supporting foil or other profiled member not requiring an additional carrier.

The examples given below lilustrate a number of compositions which have been 115 used for resistance materials according to the invention.

...

EXAMPLE 1
Resistance material consisting of: —
9620 g polystyrene 120
3500 g graphite
650 g fire soot
350 g Mobil oil "Gargoyle" Vactra 2

("Gargoyle" is a Registered Trade Mark).

This mixture was applied to a thickness of 2μ on a paper support; when a voltage

125

of 220 V was applied, the foil was heated to a maximum of about 44° C at a room

~-	-	_	

		,055,553 x	š
	temperature of 10° C. no matter how much	Example 8	
	heat transfer was blocked.	Resistance material consisting of:	
	Evalence 2	5800 g "Versamid"	60
	EXAMPLE 2	3300 g Graphite	
9	Resistance material consisting of:	3300 g powdered glass	
-	5800 g "Versamid" (Registered Trade Mark).		•
	2500 g fire soot	Application as in Example 1; maximum	:
	600 g Trafo oil	temperature reached was about 20° C, at a	65
		room temperature of 10° C.	
1/	Application as in Example 1; maximum		
10	temperature reached was about 24° C. at a	EXAMPLE 9	
	room temperature of 10° C.	Resistance material consisting of:	
	T	7500 g polystyrene	
	Example 3	3300 g graphite	70
	Resistance material consisting of: 5800 g "Versamid"	650 g fire soor	
15	3300 g vershite	400 g "Cellon" (Registered Trade	
	3300 g graphite 940 g iron powder	Mark).	
	520 g bceswax	Application as in Example 1; maximum	-
		temperature reached was about 25° C. at a room temperature of 10° C.	75
	Application as in Example 1; maximum	WHAT WE CLAIM IS:—	
20	temperature reached was about 16° C. at a	1. Electric resistance material having the	•
20	room temperature of 10° C.	following constituents: — a finely divided re-	
	Transma 4	sistance substance, an insulating material, and	80
	EXAMPLE 4 Resistance material consisting of:	a non-conductive inert carrier material, the	
	9620 g polystyrene	insulating material having a markedly higher	
	3300 g graphite	specific resistance and a greater coefficient	
25	650 g fire soot	of thermal expansion than the resistance sub-	
	450 g beeswax	stance such that when the resistance material	85
		is heated the insulating material expands to	ڄ
	Application as in Example 1; maximum	a greater extent than the resistance substance	
	temperature reached was about 27° C. at a room temperature of 10° C.	and thus increases the resistance to current	
	room temperature of 10 C.	flow between the particles of resistance sub-	
30	Example 5	stance.	90
20	Resistance material consisting of:	2. Material according to claim 1 wherein	
	5800 g "Versamid"	the resistance substance is graphite or a	
	4000 g iron powder	resistance wire alloy.	
	520 g beeswax	3. Material according to claim 1 or claim	
35	Application as in Example 1. The foil	2, wherein the resistance substance is in pul-	95
	had low conductivity and was for use at volt-	verulent form.	•
	ages e.g. above JUU V. Maximum temperature	4. Material according to any preceding	
	reached was about 27° C, at a room tempera-	claim, wherein the carrier material is a syn- thetic resin.	
	ture of 10° C.		
		5. Material according to claim 3, wherein	100
40	EXAMPLE 6	the grains of the pulverulent resistance sub- stance are enveloped by the insulating	
	Resistance material consisting of:	material.	
	5800 g "Versamid"	6. Material according to claim I wherein	,
	3300 g graphite	the insulating material is liquid below the	10Ė
45	940 g iron powder	desired maximum temperature.	105
4.5	525 g silicone oil	7. Material according to claim 6 wherein	
	Application as in Example 1; maximum	the insulating material is liquid at the desired	
	temperature reached was about 33° C. at a	working temperature.	,
50	room temperature of 10° C.	8. Material according to claim 1, wherein	110
	Evasion =	the insulating material is plastically deform-	- • •
	EXAMPLE 7 Resistance material apprint	able at the desired maximum temperature	1
	Resistance material consisting of: 9620 g polystyrene	y. Maicrial according to claim & wherein	,
	3500 g graphite	the insulating material is plastically deform-	
	650 g fire soot	able at the desired working temperature.	115
	600 g silicone oil	10. Material according to claim 1, where-	
55	Application as in Example 1; maximum	in the insulating material is powdered place	
	temperature reached was about 30° C. at a	11. Electric resistance materials substanti-	
	FORTH FEMALES AND 109 C	ally as herein described, with reference to	1
	- F 4, 10 Q,	the examples.	20

1,053,331

12. An electric resistance heating element comprising a foil of resistance material according to any preceding claim.

WITHERS & SPOONER, Chartered Patent Agents, 148—150, Holborn, London, E.C.1, Agents for the Applicants.

Leamington Spa: Printed for Her Majesty's Stationery Office by the Courier Press.—1966.
Published at The Patent Office, 25, Southampton Buildings, London, W.C.2, from which copies may be obtained